

## BP SYNTHETIC ENAMEL TO IS:2932

### USES

Recommended for use on tank exterior structural etc.

### SCOPE

BR Synthetic Enamel is translated to give a glossy durable coating meeting IS:2932 specification. It is ideally suitable for application on primed steel structures in air polluted atmosphere.

### PRODUCT DATA

TYPE	:	Single Pack
COMPOSITION	:	Modified alkyd medium suitably pigmented
APPLICATION	:	By Brush / Conventional spray as per order.
DRY FILM THICKNESS	:	25 – 35 Microns
THEORETICAL SPREAD RATE	:	11.2 – 14.0 Sq. mtr / ltr.

### DRYING TIME

TOUCH	:	3-4 Hrs.
HANDLE	:	16 Hrs.
HARD OVERNIGHT	:	20 Hrs.
OVERCOATING INTERVAL	:	Min - Overnight
FLASH POINT	:	Above 30° C
COLOUR	:	Assorted Shades
FINISH	:	Glossy
PACKING	:	20 Ltr.
STORAGE LIFE	:	Upto twelve months.

### CHEMICAL RESISTANCE

ACID	:	Satisfactory
ALKALI	:	Satisfactory
WATER	:	GOOD

### FLEXIBILITY

Excellent

### ABRASION RESISTANCE

Moderate

### HEALTH & SAFETY

Please refer to the separate Safety Data Sheet available with detailed information.

#### DISCLAIMER

This information contained within this Data Sheet is based on information believed to be reliable at the time of its preparation. The Company will not be liable for loss or damage howsoever caused including liability for negligence, which may be suffered by the user of the data contained herein. It is the users' responsibility to conduct all necessary test to confirm the suitability of any product or system for their intended use. No guarantee of results is implied since conditions of use are beyond our control.